



TULSA

Plywood

HDO 100/30

OVERLAID BOARDS FOR CONCRETE FORMING

Panel overlaid on side with film HDO 168 g/m² + 235 g/m² MDO with backer HDO 168 g/m².

GENERAL SPECIFICATIONS

Allows between 15 to 25 reuses (requires reasonable care).

Its main face has 168 g/m² high density film + 235 g/m² MDO film overlay, providing a high quality that assures water resistance, stiffness and stability, its back has 168 g/m² high density film.

65% Phenolic resin in overlay film and 27% in MDO.

PRODUCT FEATURES AND APPLICATIONS

Tulsa HDO panels are edge sealed during manufacturing. If you have to cut boards during use, it is recommended to re-seal the fresh edges to avoid panel damage caused by capillary penetration of humidity.

Make sure to also use the appropriate form remover or release agent (a chemical reactive releases for nonporous surfaces).

Although cleaning a Tulsa HDO Panel overlaid panel is much easier and quicker than traditional form material, it is important to use only fiber spatulas and synthetic materials when cleaning forms to prevent damages on the faces. This damage might occur when using metallic tools. Always store the panels inside a warehouse, protected from weather conditions.

While Tulsa HDO Overlay Panel are very resistant to the abrasion and impact, care must be taken during cleaning and use to prevent damage. Always use appropriate vibrators and techniques to protect the panel surface.

