



# TULSA

Plywood

## MDO concrete with Backer OVERLAID BOARD FOR CONCRETE FORM

### GENERAL SPECIFICATIONS

- Allows between 10 reuses (requires reasonable care).
- Main face with MDO 367 g/m<sup>2</sup> and backer 125 g/m<sup>2</sup>.
- 35% phenolic resin in MDO.

### PRODUCT FEATURES AND APPLICATIONS

Tulsa MDO Concrete Forming panels are edge sealed during manufacturing. If you have to cut boards during use, it is recommended to re-seal the fresh edges to avoid panel damage caused by capillary penetration of humidity.

Make sure to also use the appropriate form remover or release agent (a chemical reactive releases for nonporous surfaces).

Although cleaning a Tulsa MDO overlaid panel is much easier and quicker than traditional form material, it is important to only use fiber spatulas and synthetic materials when cleaning forms to prevent damages to the faces. This damage might occur when using metallic tools. Always store the panels inside a warehouse, protected from weather conditions.

While MDO Concrete Forming panels are very resistant to the abrasion and impact, care must be taken during cleaning and use to prevent damage. Always use the appropriate vibrators and techniques to protect the panel surface.

